

## The Soaring Increase of Resistant Microorganisms Demands Immediate Action Solutions are Available

J Peter Guggenbichler<sup>1\*</sup> and Sigmund Guggenbichler<sup>2</sup>

<sup>1</sup>Erlangen, Department of Pediatrics, AmiSTec GmbH und Co KG, Kössen, Austria

<sup>2</sup>Division for Vascular Surgery and Endovascular Surgery of the University Clinic for Cardiac Surgery, Vascular Surgery and Endovascular Surgery, Univ. Salzburg, Austria

### ABSTRACT

Clinical environments provide an ideal reservoir for the growth, proliferation, and transmission of pathogenic organisms. Surfaces in hospitals e.g. hospital furniture, ECG lead wires and other cables, push buttons of infusion pumps, control knobs of ventilation machines, textiles as well as implantable biomaterials like central venous catheters, urologic catheters, endotracheal tubes are contaminated increasingly frequent with multiresistant microorganisms. These microorganisms are distributed by the hands of the nursing personnel throughout the hospital with serious, life threatening consequences. 1.8 million patients suffer from a nosocomial infection per year in Europe; approximately 180,000 deaths are attributed to these infections. The Centers for Disease Control (CDC) estimates that 2 million U.S. patients per year acquire a hospital-related infection. These infections cause 90,000 deaths each year and cost an average of \$47,000 per patient to treat. The added cost to hospitals is \$4.8 billion annually for extended care treatment. Microorganisms show an increasing rate of resistance against the majority of antibiotics including carbapenems as last available antibiotic. 700,000 deaths have been reported worldwide, 30 000 deaths alone in Europe during the last year due to infections where no effective antimicrobial substance was available. The use of disinfectants is ostensibly intended to remove/kill pathogens on surfaces. However studies have shown that more than one-half the time, surfaces are not adequately cleaned or are re-contaminated within minutes. Much emphasis has been put therefore on hand disinfection. However there are also reports of the emergence of alcohol tolerant/insensitive microorganisms e.g., vancomycin resistant enterococci. This phenomenon has the potential to undermine the effectiveness of alcohol based disinfectant standard precautions. The reason for this dramatic development of resistant microorganisms is still in debate. The indiscriminate use of antibiotics for prevention of a bacterial superinfections e.g. sinusitis, otitis media after a viral infections is frequently incriminated, however this seems to have little impact on the occurrence of multi-resistant hospital pathogens in general. However individual patients are seriously affected by the selection of multi-resistant pathogens. In contrast there is increasing evidence that the widespread use of disinfectants is responsible: disinfectants - analogous to antibiotics - must be incorporated into the metabolism of microorganisms. This is inevitably associated with induction of resistance by transfer of resistance plasmids e.g. induction of efflux pumps. 10 167 publications (PubMed Jan. 2023) are available in the international literature which document the resistance of microorganisms against disinfectants; 649 publications describe the cross resistance with antibiotics, at the same time there are 11 237 publications on the toxicity of disinfectants.

### \*Corresponding author

J Peter Guggenbichler, Erlangen, Department of Pediatrics, AmiSTec GmbH und Co KG, Kössen, Austria. Tel: +43 5375 20288.

**Received:** January 14, 2023; **Accepted:** January 25, 2023; **Published:** February 20, 2023

### Introduction

For people in the 21st century, it is hard to imagine the world before antibiotics. At the beginning of the 20th century, as many as nine women out of every 1,000 who gave birth died, 40 percent from sepsis. In some cities as many as 30 percent of children died before their first birthday. One of every nine people who developed a serious skin infection died, even from something as simple as a scrape or an insect bite. Pneumonia killed 30 percent of those who contracted it; bacterial meningitis was almost universally fatal. Ear infections caused deafness; sore throats were not infrequently followed by rheumatic fever and heart failure. Surgical procedures were associated with high morbidity and mortality due to infection. This picture changed dramatically with three major developments: improvements in public health, vaccines, and antibiotics. Over the course of the 20th century, deaths from infectious diseases

declined markedly and contributed to a substantial increase in life expectancy.

Antibiotics, in particular, have saved millions of lives. But the world is now at dire risk of losing this progress. Bacteria and other microbes evolve in response to their environment and inevitably develop mechanisms to resist being killed by antibiotics but also disinfectants [1,2]. For many decades, the problem was manageable as the growth of resistance was slow and the pharmaceutical industry continued to create new antibiotics. Over the past decade, however, this brewing problem has become a crisis. The evolution of antibiotic resistance is now occurring at an alarming rate and is outpacing the development of new countermeasures capable of thwarting infections in humans [3,4]. This situation threatens patient care, economic growth, public

health, agriculture, economic security, and national security. The UN Interagency Coordination Group on Antimicrobial Resistance demands therefore immediate, coordinate and ambitious measures to combat this problem [5].

**There Are Several Reasons Described For This Problems**

1) Indiscriminate use of antibiotics for viral infections has been incriminated. However, these reasons – although important - contribute only moderately to the dramatic increased emergence of resistant microorganisms although highly relevance for the individual patient. Many patients receiving prophylactic antibiotics to prevent a bacterial infection (sinusitis, otitis media, pneumonia) suffered in spite of this a bacterial infection although with a multiresistant microorganism which required even i.v. antibiotics.

Viral infections of the upper respiratory tract are frequently observed in children and predispose patients for bacterial superinfections e.g. sinusitis, otitis media or bronchitis, rarely pneumonia or a bloodstream infections where the administration of antibiotics is mandatory [6,7]. Antibiotics have to be administered only once a bacterial superinfection has been documented. This requires frequent clinical controls of the patient. Prophylactic antibiotics are not helpful for the prevention of these bacterial superinfections; in essence they also complicate the treatment of these infections as already resistant microorganisms may have been selected in the oral/nasal flora within a few days. Prophylaxis of bacterial superinfections is feasible with an approach other than antibiotics. Effective alternatives are e.g. anti-inflammatory properties based on herbal extracts (thyme, gentian, primula) which open clogged paranasal sinus openings as well as the patency of the Eustachian tube and improve the mucociliary clearance. These herbal extracts decrease the arachidonic acid metabolism, the precursor of proinflammatory cytokines [8]. This has been documented beyond reasonable doubt by prospective, randomised double blinded studies that herbal extracts are by far superior to the prophylactic administration of antibiotics for prevention of bacterial superinfections due to respiratory viral infections [9].

**2) Administration of antibiotics in animal husbandry**

The use of antibiotics in animal health seems to be an important reason for the development of resistant microorganisms. Antibiotic-resistant bacteria associated with animals may be pathogenic to humans, easily transmitted to humans via food chains, and widely disseminated in the environment via animal wastes. There are however additional facets to be considered. Antibiotics are generally not found in meat except in broilers as non absorbable antibiotics e.g. colistin are used [10].


The problem is the selection of resistant microorganisms in the excretions which are usually distributed into the environment as fertilisers [11]. Vegetables harvested on these fields are frequently contaminated. The majority of remaining microorganisms on vegetables is eradicated by the hydrochloric acid in the stomach. Some microorganisms escape and are found in the flora of the large intestine in low concentrations. There these resistant microorganisms are under control of a stabile faecal flora. However if a broad spectrum antibiotic is administered to the patient, the sensitive flora is eliminated and the resistant microorganisms prevail.

There is also a solution for elimination of prophylactic antibiotics as growth enhancers. The pathogenic property of microorganisms responsible for nosocomial infections is the formation of toxins of

the pathogen but also - equally important - adherence on epithelial cells [12]. The blockage of adherence of microorganisms on epithelial cells by receptor analogue carbohydrates i.e. acid galacturonides is an important treatment option and can prevent the use of antibiotics. Animal studies demonstrate superior outcomes of this option compared to antibiotics without induction of resistance.

**Table 1: Frequency of Diarrhea in Weaning Piglets**

	Diarrhea	no diarrhea	Total number
Galacturonides	10 14,7%	58 85,3%	68 100%
Control	31 50,0%	31 50,0%	62 100%
Tylosine phosphate	17 24,6%	52 75,4%	69 100%
Total number	58 29,1%	141 70,9%	199 100%



Acid galacturonides have also been effectively used to prevent the death of chicken in a laying hen battery and pore egg quality in a controlled investigation.

The lack of attention of pharmacodynamic and pharmacokinetic properties of new antibiotics by regulatory authorities is a severe shortcoming. Broad spectrum antibiotics with incomplete bioavailability (Cefixim) or prodrugs with predominant biliary elimination (Cefuroxime proxetil) select multi resistant microorganisms in the faecal flora just as i.v. Ceftriaxone with a 75% biliary elimination. Azithromycin has an elimination half-life of 68 hours [13]. Subinhibitory concentration in the oral cavity over 3 weeks select invariably high numbers of macrolide resistant microorganisms in contrast with Clarithromycin with a half-life of 2 hours. Macrolide insensitive microorganisms after administration of Azithromycin are also distributed to all classmates in Kindergarten [14,15].

The emergence of multi resistant microorganisms however developed into a dramatic situation. Biofilm formation and subinhibitory concentrations of disinfectants contribute to this phenomenon [16-17]. Microorganisms in a biofilm can not be eliminated by agents which have to be incorporate into the metabolism of microorganisms as microorganisms in a biofilm are hibernating and don't take up anything from the environment. The fact VBNC (viable but not culturable) contributes to the confusion as microorganisms in a biofilm require special culture methods for detection.

More than 8000 publications in the international literature (PubMed) describe the resistance of microorganisms against

disinfectants and in addition 803 publications describe the cross resistance with antibiotics. At the same time there are 11 229 publications describing the toxicity of disinfectants. Contaminated surfaces contribute substantially to the transmission of hospital pathogens and the spread of multi resistant microorganisms [18]. Disinfection of surfaces with disinfectants is not constructive any more as ample evidence exists for tolerance of microorganisms to sublethal levels of various disinfectants e.g. quaternary ammonium compounds (QAC) i.e. benzalkonium chloride as well as chlorhexidine, hexadecylpyridinium and cetrimide [19]. The resistance of QAC based disinfectants to antibiotics is conferred by the resistance determinants *qacH* and *bcrABC*. The presence and distribution of these genes have been anticipated to assume a role in the survival and growth of various microorganisms. It has been described that disinfectants e.g. Triclosan, Benzalkonium chloride even enhances the growth of *Listeria monocytogenes* in the food industry [20,21].

The use of disinfectants - ostensibly intended to remove/kill pathogens on surfaces which are ubiquitously contaminated with microorganisms - is not reliable anymore. Studies have shown that more than one-half the time, microorganisms on these surfaces are not adequately eradicated or surfaces are recontaminated within minutes. These frequently multiresistant microorganisms are distributed within the hospital by the hands of the personnel to patients. A microbial burden of >8000 CFU on a 100 cm<sup>2</sup> surface is associated with an incidence of 21 % of a hospital acquired infection. In reality we see 100 – 1000 time higher inoculum sizes. Much emphasis has been put therefore on hand disinfection. However, there are also reports of the emergence of alcohol tolerant/insensitive microorganisms e.g. vancomycin resistant enterococci after extensive hand disinfection [22]. This phenomenon has the potential to undermine the effectiveness of alcohol-based disinfectant standard precautions [23]. This prompted the WHO to publish a warning of an imminent crisis due to the lack of effective antibiotics and requests immediate, coordinate and ambitious measure. An entirely new approach must be instituted [5].

Considering the above information it was mandatory to reassess preventive measures for hospital acquired infections and to curb the dramatic increasing rate of emerging resistant microorganisms. Antimicrobial coatings hold promise based, in essence, on the application of materials and chemicals with persistent bactericidal or -static properties onto surfaces or in textiles used in the healthcare environments.

#### **A Number of Technologies Have Been Proposed**

This belief is based on some preliminary studies involving, for example copper and silver ions, titanium or organosilane, albeit under laboratory conditions. However, the definitive evidence as to their efficacy is still lacking. There are however also several shortcomings of these technologies. Active drug eluting agents (e.g. ions or (nano) particles of silver, copper, zinc, or antibiotics, chloride, iodine) are incorporated into the metabolism of microorganisms and must be eluted from the polymer of the surface: This shows crucial disadvantages: The activity of e.g. silver ions is limited to a short period of time as not sufficient concentrations of silver can be incorporated into a surface. For silver this means a duration of activity of 3 weeks [24-28].

Copper endowment of a surface has been investigated and preliminary results show a substantial reduction in the number of HAI which establishes the proof of concept. However adverse events have been observed. Besides copper has a poor antimicrobial activity. This activity is somewhat improved by

alloys e.g. combination with zinc or tin but still does not meet the requirements.

The antimicrobial activity of a copper surfaces is not sufficient!

- Copper is cytotoxic if in use for implantable biomaterials.
- The surfaces are rapidly oxidized and require continuous cleaning.
- Copper cannot be used in cable insulations
- Copper cannot be used as transparent coatings of surfaces.
- Hospital surfaces are preferably white, the color of copper is not accepted by the majority of patients
- The antimicrobial activity is in comparison with the antimicrobial activity of catalysts by far inferior.

Additional technologies with limited usefulness or profound toxicity e.g. Ruthenium, and allergisation e.g. nickelous hydroxide have been propagated.

Multi-drug resistant (MDR) bacteria have been reported as contaminating microorganisms of surfaces, commonly used medical equipment and high-contact communal surfaces (e.g., telephones, keyboard, medical charts) in a hospital. Contamination of inanimate surfaces in ICU has been identified in outbreaks and cross-transmission of pathogens among critically ill patients. Inanimate surfaces and equipment (e.g., bedrails, stethoscopes, medical charts, ultrasound machine) are frequently contaminated by bacteria, including MDR isolates. The development of self-sanitizing surfaces with a broad spectrum of activity, long lasting to permanent antimicrobial activity without induction of resistance seems to be a promising solution for this problem if the requirements for the prevention of hospital acquired infections are met. Contamination may occur either by transfer of microorganisms contaminating healthcare workers' hands or direct patient shedding of microorganisms in the immediate environment of a patient's bed. Inadequate hygiene in hospitals has a proven impact on the development of resistant microorganisms. However strong emphasis, based on alcoholic hand hygiene, has been reported responsible for a massive increase of vancomycin resistant and alcohol insensitive enterococci [29].

The most important reason for this dreadful development is the use of disinfectants. Disinfectants are widely used for elimination of microorganisms from a surface but proved to be a not reliable method any more due to a substantial increase of multi-resistant microorganisms against disinfectants and cross resistance with antibiotics. It has been reported that both Gram-positive and Gram-negative bacteria are able to survive up to months on dry inanimate surfaces, with even longer persistence under humid and lower temperature conditions. Environmental contamination by fungi and viral pathogens including coronavirus has been also described on surfaces in frequented customer areas viable for weeks. Factors that may affect the transfer of microorganisms from one surface to another and cross-contamination rates are type of organisms, source and destination of surfaces, humidity level, and size of inoculum [30-32]. The development of self-sanitizing surfaces with a broad spectrum of activity, fast eradication of microorganisms, long lasting to permanent antimicrobial activity without induction of resistance is the only promising solution for this problem if all the requirements for the prevention of hospital acquired infections are met.

**The requirements of self-sanitizing surfaces** for the prevention of hospital acquired infections in hospitals, public transportation, the food industry are extraordinary high.

- Intensive, fast and broad antimicrobial activity, against Gram-positive, Gram-negative microorganisms, irrespective of

their antibiotic susceptibility, fungi, legionella, molds, viral pathogens e.g. influenza including COVID 19 documented by the RODAC plate method

- Fast eradication of microorganisms i.e. minimum 5 log 10 reduction within 30 minutes.
- Activity against a high inoculum size of 10<sup>9</sup> CFU on an area of 3 cm<sup>2</sup>
- No induction of resistance
- Nontoxic, skin and soft tissue compatibility, no allergenicity, sbD (safe by design)
- Long lasting/permanent antimicrobial activity water-, acid-, alkaline-, alcohol insoluble, UV light stabile
- Cleanable with detergents
- Uncomplicated technical processability, heat stabile up to 400°C, non corrosive
- Physical stability, activity irrespective of sweat, grease, blood, pus
- Not flammable, smoke reduction
- BP authorisation by the European commission on biocidal products.
- Favourable cost/benefit analysis

To combat multi-drug resistant (MDR) superbugs, a plethora of novel methods are under investigation, while old and momentarily forgotten strategies (nano-compounds, bacteriophages, physical factors) are being revised. There are however several shortcomings of these technologies [33-35].

Physical factors, such as UV light, high steam temperature have been propagated, especially in industries with a high risk of microbial contamination. UV light could kill a wide array of microorganisms including both vegetative and spore forming pathogens by induction of oxygen radicals. However the activity is often not sufficient for bacterial eradication and has a number of adverse events like skin and eye problems and carcinogenicity. Considerable variabilities in duration and the distance of the light emitting source have been determined [36].

Steam shows an immediate germfree surface – however it does not exhibit a lasting antimicrobial activity. If someone touches the surface after 10 minutes, the surface is contaminated again. The steam technology would have to be reapplied in frequent i.e. in 30 minutes intervals. Various technologies with a potential to curb the dramatic increase of multiresistant microorganisms have been described.

Since the early 1900s, bacteriophages are recommended for medical purposes. Several companies and research laboratories pursue a treatment strategy involving phages in infections caused by *Staphylococcus aureus*, *Pseudomonas aeruginosa*, and *Escherichia coli* [37]. In some countries (e.g., Russia, Georgia, Poland, USA), bacteria which do not respond to conventional antibiotics are treated by phages. The problem with phages is their specific activity against a certain bacterium. This requires the identification of the microorganisms prior to the application and selection of the suitable phage among thousands of phages. A possible solution might be the use of a phage cocktail containing a multitude of different phages. Phages are not heat resistant and can therefore not be incorporated into polymers [38].

There are high expectations of the efficient killing of bacteria using nanostructures and their non-chemical mechanisms such as contact killing, mechanical puncturing, and changes in the local microenvironment via nano-ions [39]. Combination with metal oxides, silver, chitosan, gallic acid nanoparticles etc. have


also been recommended. Addition of silver is a feasible approach but - as already described - only free silver ions are active – in other words silver has to be released from the hydrophilic bottom layer and incorporated into the bacterial metabolism. The duration of antimicrobial activity is therefore limited to maximum of 14 days. Nanoparticles combined with antibacterial agents are also being studied [39]. Antibiotics and disinfectants however are not suitable for providing a permanent endowment of surfaces with antimicrobial properties. The induction of resistant microorganisms has been described and is of great concern.

The activity of a technology on the basis of Titanium oxide can only be documented with the JIS 25923 method where the activity is determined in the capillary space between the surface and a foil which prevents the evaporation of oxygen radicals. The determination of antimicrobial activity by the RODAC plate methods shows no efficacy! This method lacks clinical relevance.


In situ generated biocides by catalysts (molybdenum oxide, tungsten blue oxide, Zinc molybdate and polyoxometallates) show fast antimicrobial activity against a very broad spectrum of bacterial pathogens including microorganisms embedded in a biofilm, fungi, moulds and several viral pathogens including COVID 19 on surfaces. Transition metal oxides can be incorporated into various coatings and polymers, they are water insoluble and have a documented duration of activity of at least 10 years and 10 000 cleanings. Transition metal oxides are not toxic, there is no induction of resistance. The activity and marketability has been documented by external laboratories and the BPR of the EU [40,41].

In situ generated biocides on surfaces by transition metal oxides meet all the requirements described above. Surfaces decorated with metal oxides eg. Lewis acids such as MoO<sub>3</sub>, oxygen deficient tungsten blue oxide WO<sub>3</sub> and Zinc molybdate have also shown a broad-band and strong antimicrobial activity resulting in a reduction of the number of colony forming units by 6 – 7 log 10 within 1-3 hours. Their mechanism of action is based on the in-situ generation of 4 mechanisms which work in a synergistic mode.

a) H<sub>3</sub>O<sup>+</sup> ions through the reaction with moisture from the air inspired by the body's own defense mechanism imitating e.g. the acid coating of the skin. The resulting acidified surfaces have a pH of 4.5 and the H<sub>3</sub>O<sup>+</sup> ions are able to diffuse through the cell membranes where they can distort the pH-equilibrium and transport systems of the pathogen. Due to the Zeeman effect acid water molecules remain on the surface!



b) In addition to this mechanism also free radicals e.g. oxygen radicals and hydroxyl radicals are formed which result in a synergistic mode of action.




Transition metal oxides embedded in polymers Transition oxides embedded in coatings

c) A positive zeta potential has also been determined limited at a μm distance at the surface. This is reflected by an extraordinary fast eradication of microorganisms i.e. a reduction of 5 log 10 within 15 minutes documented by laser scanning microscopy [40].

d) Last not least paramagnetic Ions also contribute to the antimicrobial activity [41].



This technology is the only one which meets all the requirements described initially for prevention of Hospital acquired infections. The additives are water, detergent and alcohol insoluble and are fixed in a polymer or a coating where they are not eluted. There is no induction of resistance, no allergenicity, the additives are nontoxic and are essential trace elements in the body! Long lasting (>10 years) antimicrobial activity – including activity against microorganisms in biofilms - has been documented.



Easy cleaning has been documented with water and detergents as microorganisms don't adhere on acid surfaces. 1000 cleanings with water and a detergent did not impair the antimicrobial activity of this technology.

The technology is also active against microorganisms embedded in a biofilm! Microorganisms in a biofilm are hibernating and don't take up anything from the outside. Therefore all technologies which are based on incorporation of the antimicrobial agent into the bacterial metabolism are ineffective against microorganisms in a biofilm. Again technologies which attack microorganisms from the outside also eradicate microorganisms in a biofilm, an important asset. However also technologies based on oxygen radicals alone are also not sufficiently active as these free radicals are not able to penetrate the biofilm. This has been described for Titanium oxide.

The antimicrobial technology of this technology is approved by the BPR of the EU as in situ generated biocides and is legitimately on the market. As these additives are not eluted to the surface, no toxicity is observed. Molybdenum is an essential trace element in the body as stabilizing molecule for several enzyme systems responsible e.g. for the elimination of sulfur in the body.

The antimicrobial activity and marketability of these in situ generated biocides has been documented by the Austrian ministry of environmental protection as rapporteur of the BPR of the EU. Since the application for active substance approval for the "free radicals" was submitted according to Art. 93 Biocidal Products Regulation and before 1.9.2016, the transitional periods of Art. 89 (2) apply, i.e. both biocidal products and treated goods may be legally made available on the market during the active substance evaluation.

In the future no easy approval for "in situ generated biocides" is possible by ECHA. This opportunity expired September 1, 2018. As the application as biocidal product it is under a special legislation with documentation of several additional facets (duration of antimicrobial activity > 5 years, activity despite of soiling, no nanoparticles, activity against microorganisms in a biofilm as the additives don't have to be incorporated into the bacterial metabolism) this is also an additional favorable asset of the presently available technology.

### Available products

Four additives are available as in situ generated biocides with important additional properties

a) Molybdenum oxide. Molybdenum is incorporated in thermoplastic polyurethane in use for antimicrobial ECG lead wires. The antimicrobial activity has been documented: Immersion in 10<sup>9</sup> CFU/ml for 6 hours shows no growth at the surface after application on blood agar plates. The duration of the antimicrobial activity is more than 20 years. The results of numerous external investigations are available. Additional application in push buttons, artificial leather with a blue grayish appearance has been endowed with molybdenum oxide. The advantage Molybdenum oxide is an inexpensive additive, readily available in unlimited quantities.

b) 5 % Oxygen deficient Tungsten blue oxide is in use for surfaces in permanent contact with water e.g. pipes faucets in hospitals. This can prevent the growth of legionella in faucets. The endowment of water heaters e.g. incorporated into enamel has also be investigated providing a permanent coating. Oxygen saturate tungsten yellow oxide shows limited antimicrobial activity.

c) The incorporation of Molybdenum into the zinc oxide crystal lattice results in a highly active white or - with submicron particles - transparent coating or paint. Zinc Molybdate has broad application for hospital furniture, for leather, textiles or artificial leather in numerous applications also in public transportation, for office furniture in contact with different customers. The antimicrobial activity is very broad including a number of viral pathogens like bird flu, swine flu, influenza, Herpes, Epstein Barr virus. Transparent coatings are available with particle sizes of the additives e.g. Zinc Molybdate of 0.20 µm (Lambda half) [42-44].

d) The incorporation of Molybdenum oxide into the tungsten crystal lattice provides additional antimicrobial features due to a strong zeta potential: The antimicrobial activity against bacterial pathogens is fast and includes fungi and molds (*Aspergillus* spp), the majority of viral pathogens like hepatitis B, C, COVID 19. In contrast to previous believe that COVID 19 is only transmitted by droplets, pertinent literature also incriminates surfaces as a source of COVID transmission:

Human-to-human transmission is the main route of infection, presenting a substantial threat of rapid spread of the virus

throughout the community [45]. It is documented that also persons with mild or clinically unapparent disease can spread the virus. However, as a greater understanding of the virus is achieved, the routes of transmission have been widened by the WHO to include possible human-human contact, droplet, airborne, fomite, fecal-oral, bloodborne, mother-to-child and animal-to-human transmission. Increasing concern of contact transmission during outbreaks has been cited. Viruses are spread by droplets expelled by coughs and sneezes, which can contaminate surfaces. Ample evidence in the literature indicates that pathogenic human coronavirus contaminate the environment 2 m to 6 m away, respectively, and a single droplet may easily contain an infectious dose. Viral pathogens are surviving on a surface if epithelial cell material is contained in the droplets for an extended period of time [46]. There are reports of a human lung cell culture model show persistence of infectious viral particles at least 5 days of on a range of common nonbiocidal surface materials, including polytetrafluoroethylene (Teflon; PTFE), polyvinyl chloride (PVC), ceramic tiles, glass, silicone rubber and stainless steel. Investigations of the antimicrobial activity against COVID 19 has been performed by the MSL laboratory: The test product received has achieved a 99.22 % reduction of feline coronavirus under the conditions stipulated. Documents MSL Laboratories, Gollinrod UK. There is also a strong activity against algae providing antifouling surfaces for marine vessels.

e) All additives can be used as transparent coating or paints if applied as submicron particle sizes (lambda half) However great caution has to be exhibited to leave the delicate orthorhombic and monocline crystal structure intact. These particles with a size of 0.2  $\mu\text{m}$  can be achieved by thermal fracturing.

f) The surface must be "wetable" i.e. hydrophilic with a contact angle of 30° or less. Numerous hydrophilising agents have been investigated. Sorbitol alcohol is one of these compounds but this is water soluble and exerts only hydrophilicity for a limited period of time. Preferable is e.g. crodamol, feroxacin, lubrophos and various Tween compounds.

## Summary

In situ generated biocides on the basis of transition metal oxides provide a strong, fast and broad antimicrobial activity against Gram positive, gram negative antimicrobial activity regardless of their antimicrobial susceptibility, fungi, virus including COVID 19. The activity is long lasting (> 10 years documented) There is no toxicity, nor induction of resistant microorganisms is observed. Transition metal oxides (catalysts) can be applied to almost every polymer or coating also retrospectively [46].

## References

1. Vincent JL, Rello J, Marshall J, Silva E, Anzueto A, et al. (2009) International study of the prevalence and outcomes of infection in intensive care units. *JAMA* 302: 2323-2329.
2. Rusotto V, Cortegiani A, Graziano G, Saporito L, Raineri SM, et al. (2015) Bloodstream infections in intensive care unit patients: distribution and antibiotic resistance of bacteria. *Infect. Drug Resist* 8: 287.
3. Plipat N, Spicknall IH, Koopman JS, Eisenberg JN (2013) The dynamics of methicillin-resistant *Staphylococcus aureus* exposure in a hospital model and the potential for environmental intervention. *BMC Infect Dis* 13: 595.
4. Fair R, Tor Y (2014) Antibiotics and Bacterial Resistance in the 21st Century. *Perspect Medicine, Chem* 6: 25-64.
5. Expertengruppe WHO: UN Interagency Coordination Group

- on Antimicrobial Resistance <https://www.aerzteblatt.de>
6. Itzhak Brook (2013) Acute sinusitis in children. *Pediatr Clin North Am* 60: 409-424.
7. Magalhães C, Lima M, Trieu-Cuot P, Ferreira P (2021) To give or not to give antibiotics is not the only question. *Lancet Infect Dis* 21: e191-e201.
8. Han D, Wang N, Zhang L (2009) The effect of myrtol standardized on human nasal ciliary beat frequency and mucociliary transport time. *Am J Rhinol Allergy* 23: 610-614.
9. Smith HS (2006) Arachidonic acid pathways in nociception. *J Support Oncol* 6: 277-287.
10. Lees P, Pelligand L, Giraud E, Toutain PL (2021) J A history of antimicrobial drugs in animals: Evolution and revolution. *Vet Pharmacol Ther* 44: 137-171.
11. Roth N, Käsbohrer A, Mayrhofer S, Zitz U, Hofacre C, et al. (2019) The application of antibiotics in broiler production and the resulting antibiotic resistance in *Escherichia coli*: A global overview *Poult Sci* 98: 1791-1804.
12. Kastner U, Glasl S, Follrich B, Guggenbichler JP, Jurenitsch J (2002) Acid oligosaccharides as the active principle of aqueous carrot extracts for prevention and therapy of gastrointestinal infections. *Wien Med Wochenschr* 152: 379-378.
13. Guggenbichler JP, Kofler J, Allerberger F (1985) The influence of third-generation cephalosporins on the aerobic intestinal flora. *Infection* 13: S137-939.
14. Kastner U, Guggenbichler JP (2001) Influence of macrolide antibiotics on promotion of resistance in the oral flora of children Influence of macrolide antibiotics on promotion of resistance in the oral flora of children. *Infection* 29: 251-256.
15. Kastner U, Guggenbichler J P (2001) Influence of macrolide antibiotics on promotion of resistance in the oral flora of children *Infection* 29: 251-256.
16. Rather MA, Gupta K, Mandal M (2021) Braz J Microbial biofilm: formation, architecture, antibiotic resistance, and control strategies. *Microbiol* 52: 1701-1705.
17. Fagerlund A , Langsrud S , Even H , Mikkelsen MI , Møretrø T (2016) Biofilm Matrix Composition Affects the Susceptibility of Food Associated Staphylococci to Cleaning and Disinfection Agents *Front Microbiol* 7: 856.
18. Protano C, Cammalleri V, Romano Spica V, Valeriani F, Vitali M (2019) Hospital environment as a reservoir for cross transmission: cleaning and disinfection procedures. *Ann Ig* 31: 436-448.
19. Lemmen SW, Häfner H, Zolldann D, Stanzel S, Lütticken R (2004) Distribution of multi-resistant Gram negative versus Gram-positive bacteria in the hospital inanimate environment. *R. J Hosp Infect* 56: 191-197.
20. Wang R, van Dorp L, Shaw LP, Bradley P, Wang Q, et al. (2018) The global distribution and spread of the mobilized colistin resistance gene *mcr-1*. *Nat Commun* 9: 1179.
21. Fernandes P, Ferreira BS (2003) Cabral Solvent tolerance in bacteria: role of efflux pumps and cross-resistance with antibiotics. *JM. Int J Antimicrob Agents* 22: 211-216.
22. Fernando SA, Gray TJ, Gottlieb T (2017) Healthcare-acquired infections: prevention strategies. *Intern Med J* 47: 1341-1351.
23. <https://www.srf.ch/news/p/schweizweit-groesster-fall-eines-multiresistenten-spitalkeims>.
24. Guggenbichler S, Hell M, Guggenbichler JP (2020) Hospital Acquired Infections with multiresistant Microorganisms: Can We Escape the Postantibiotic Era?. *Journal Biomedical Research*.
25. Backx BP, Dos Santos MS, Dos Santos OAL, Filho SA (2021) The Role of Biosynthesized Silver Nanoparticles

- in Antimicrobial Mechanisms. *Curr Pharm Biotechnol* 22: 762-772.
26. Strzałka W, Zglobicki P, Kowalska E, Bazant A, Dziga D, et al. (2020) The Dark Side of UV-Induced DNA Lesion Repair. *Genes (Basel)* 11:1450.
  27. Monteiro R, Pires DP, Costa AR, Azeredo J (2019) Trends Microbiol Phage Therapy: Going Temperate? *27*: 368-378.
  28. Herridge WP, Shibu P, O'Shea J, Brook TC, Hoyles L (2020) Bacteriophages of *Klebsiella* spp., their diversity and potential therapeutic uses. *J Med Microbiol* 69: 176-194.
  29. Bartkowski M, Giordani S (2020) Supramolecular chemistry of carbon nano-ions. *Nanoscale* 12: 9352.
  30. Allahverdiyev AM, Kon KV, Abamor ES, Bagirova M, Rafailovich M (2011) Coping with antibiotic resistance: combining nanoparticles with antibiotics and other antimicrobial agents. *Expert Rev Anti Infect Ther* 9: 1035-1052.
  31. Fathizadeh H, Maroufi P, Momen, Heravi MS, Köse S, et al. (2020) Protection and disinfection policies against SARS-CoV-2 (COVID-19) *Infec Med* 28: 185-191.
  32. Rai NK, Ashok A, Akondi BR (2020) Consequences of chemical impact of disinfectants: safe preventive measures against COVID-19. *Crit Rev Toxicol* 50: 513-520.
  33. Guggenbichler JP (2021) Preventing the Spread of Coronavirus on Surfaces *Journal Biomedical research* 10.26717/BJSTR.2021.33.005380
  34. Zollfrank C, Gutbrod K, Wechsler P, Guggenbichler JP (2012) Antimicrobial activity of transition metal acid MoO(3) prevents microbial growth on material surfaces. *Mater Sci Eng C Mater Biol Appl* 32: 47-54.
  35. Lackner M, Maninger S, Guggenbichler JP (2013) Saure Oberflächen als neuartige Kontaktbiozide. *Nachr Chem* 61: 112-115.
  36. Booth IR (1985) Regulation of Cytoplasmic pH in Bacteria. *Microbiological Reviews* 49: 359-378.
  37. Chang RYK, Nang SC, Chan HK, Li J (2022) Novel antimicrobial agents for combating antibiotic-resistant bacteria. *Adv Drug Deliv Rev* 187: 11437.
  38. Matsumoto KI, Ueno M, Shoji Y, Nakanishi I (2021) Heavy-ion beam-induced reactive oxygen species and redox reactions. *Free Radic Res* 55: 450-460.
  39. Grill A, Mairhofer A, Schilcher K (2018) Krankenhausinfektionen. Poster FH Oberösterreich.
  40. Doane TL, Chuang CH, Hill RJ, Burda C (2012) Nanoparticle zeta -potentials. *Acc Chem Res* 45: 317-326.
  41. Chen L, Duan J, Du P, Sun W, Lai B, et al. (2022) Accurate identification of radicals by in-situ electron paramagnetic resonance in ultraviolet-based homogenous advanced oxidation processes. *Water Res* 221: 118747.
  42. Alavi M, Kamarasu P, Mc Clements DJ, Moore MD (2022) Metal and metal oxide-based antiviral nanoparticles: Properties, mechanisms of action, and applications. *Adv Colloid Interface Sci* 306: 102726.
  43. Liu J, Liao X, Qian S, Yuan J, Wang F, et al. (2020) Community Transmission of Severe Acute Respiratory Syndrome Coronavirus 2, Shenzhen, China, 2020. *Emerg Infect Dis* 26: 1320-1323.
  44. Ge ZY, Yang LM, Xia JJ, Fu XH, Zhang YZ (2020) Possible aerosol transmission of COVID-19 and special precautions in dentistry. *Zhejiang Univ Sci B* 21: 361-368.
  45. Colović MB, Lacković M, Lalatović J, Mougharbel AS, Kortz U, et al. (2020) Polyoxometalates in Biomedicine: Update and Overview. *Curr Med Chem* 27: 362-379.
  46. Toxicological Risks of selected flame-Retardant Chemicals (2014) National Academic Press.

**Copyright:** ©2023 J Peter Guggenbichler. This is an open-access article distributed under the terms of the Creative Commons Attribution License, which permits unrestricted use, distribution, and reproduction in any medium, provided the original author and source are credited.